

XYLAN® 5230 GRAY BLACK

Chrome-Free Fastener-Class Coating

General Description

Xylan 5230 Gray Black is a "chrome-free" fastener coating material developed for the worldwide automotive market. It is a resin-bonded, thermally-cured fluoropolymer coating. Xylan 5230 is formulated for application to fasteners by dip/spin or hand-spray method. Its primary function is to facilitate uniform driving torque while providing corrosion resistance.

Substrate Information

Xylan 5230 can be applied to many types of substrate materials such as aluminum, brass, high-alloy steel, carbon steel, stainless steel, titanium, zinc plating and zinc phosphate.

Corrosion Resistance

Xylan 5230 applied in two coats (0.6 mil) over zinc-phosphated carbon steel exceeds 336 hours in ASTM B117. With three coats, it is not uncommon for testing to run 600+ hours.

Physical Properties

Pencil hardness	2 - 4 H
Dielectric strength	500 V/mil
VOC content/series avg.	4.47lbs/gal (535gms/l)
Gloss	low
UV resistance	fair

Use Temperature

Xylan 5230 can be used continuously from -70°F/-57°C to +350°F/175°C and can survive up to +425°F/218°C intermittently.

Chemical Resistance

Xylan 5230 is resistant to most automotive fuels, lubricants and fluids. It has excellent resistance to acids and alkalines.

Applicable Specifications

Xylan 5230 is an approved coating material for the following specifications:

- Daimler/Chrysler Corporation: PS-7001
- Ford Motor Company:
WSD M21 P10 B2 (S303);
WSD M21 P10 B3 (S306)
- General Motors: 6046M

Application Instructions

Please refer to the Whitford Product Data Sheet for application information or contact your Whitford representative for more information.

Performance Characteristics

- Meets SAE/USCAR 1 (336+ hours)
- Self-lubricated
- WZ100 - "K" factor .17 +/- .02 @ 28.3 kN
- Thickness - 16-20 microns
- Dry-to-touch
- Chemical-resistant
- Low risk for hydrogen embrittlement

Advantages

- Integral friction modification
- Plastic-compatible
- Cr⁺⁶ free
- Compatible with thread adhesives and sealants.
- Globally accepted
- Controlled applicator base

Whitford

Whitford Corporation, Box 2347, West Chester, PA 19380

Tel: (610) 296-3200 • Fax: (610) 647-4849 • Email: sales@whitfordww.com • website: www.whitfordww.com

Non Warranty: The information presented in this publication is based upon the research and experience of Whitford. No representation or warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Whitford makes no warranty or representation of any kind, express or implied, including without limitation any warranty of merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Whitford are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose particular to the buyer is for the buyer to determine. Whitford assumes no responsibility for the selection of products suitable to the particular purposes of any particular buyer. Whitford shall in no event be liable for any special, incidental or consequential damages.

Xylan is a registered trademark of Whitford.