

Issuer	Specification	Surface	Base	Passivation	Dörken-Product	Coating thickness / weight	Corrosion protection against	
							white	red
Acciona windpower	CS0129		Zinc flake		DELTA® -TONE 9000 + DELTA®-SEAL	4-8µm Basecoat + 8-16µm Topcoat		
Gamesa Eólica	EQ630001	C3	Zinc flake		DELTA® -TONE 9000 + DELTA-PROTEKT® / DELTA® -TONE 9000			480h
		C4	Zinc flake		DELTA® -TONE 9000 + DELTA-PROTEKT® / DELTA® -TONE 9000			720h
		C5-M	Zinc flake		DELTA® -TONE 9000 + DELTA-PROTEKT® / DELTA® -TONE 9000			1440h
GE - General Electrics	P14A-AL-0218	two layer class A	Zinc flake		DELTA® -TONE 9000 + DELTA®-SEAL GZ black	10-15µm Basecoat + 5-10µm Topcoat		min. 1000h
		single layer class B	Zinc flake		DELTA® -TONE 9000	12-25µm		min. 1000h
Kenersys	KSY_SPC_bolt		Zinc flake		DELTA-PROTEKT® KL 100 + DELTA-PROTEKT® VH 301 GZ			min. 1000h
Suzlon AE Rotortechnik	M0606600		Zinc flake		DELTA® -TONE 9000 + DELTA®-SEAL silver	6-9µm Basecoat + 6-9µm Topcoat		480h
Vestas	900182	≥ M20	Zinc flake		DELTA® -TONE 9000 + DELTA®-SEAL GZ silver	6-9µm Basecoat + 6-9µm Topcoat		816h
		= M16	Zinc flake		DELTA® -TONE 9000 + DELTA®-SEAL GZ silver	6-9µm Basecoat + 6-9µm Topcoat		600h
		= M12	Zinc flake		DELTA® -TONE 9000	9-12µm		480h
		≤ M10	Zinc flake		DELTA® -TONE 9000	6-9µm		240h
W2E - Wind to Energy	W0402-G03-DASH-304-W2E-001-1-GE	DT/DS	Zinc flake		DELTA® -TONE 9000 + DELTA®-SEAL GZ black	15-25µm		720h
		anchor bolts, Blade- and Pitch-bearing bolts	Zinc flake		DELTA® -TONE 9000 + DELTA®-SEAL GZ black	15-25µm		1000h